



**TECHNICAL DATA SHEET**

**AMBER ALUMINIUM H.T. 600°C**

<b>PRODUCT DESCRIPTION</b>	A heat resistant modified silicon based aluminium paint for atmospheric exposure conditions, having good weather resistance. It has good flow and leveling and has heat resistance up to 600°C. It should preferably be applied by spray to get the best results. An initial minimum temperature of 200°C is required to initiate the cure of the film.
----------------------------	---

<b>RECOMMENDED USES</b>	A heat resisting paint for steel structure, pipes, power stations, high temperature stacks, boilers, engines, exhaust lines, etc. where heat resistance up to 600°C is required.
-------------------------	--

**TECHNICAL DATA**

<b>COLOUR, DRY FILM</b>	ALUMINUM
<b>FINISH, DRY FILM</b>	Metallic / Lustrous
<b>VOLUME SOLIDS (ASTM D2697)</b>	24 ± 2%
<b>SPECIFIC GRAVITY</b>	0.98 ± 0.05
<b>THEORETICAL SPREADING</b>	8 M <sup>2</sup> /LTR
<b>RECOMMENDED DFT RANGE (DRY FILM THICKNESS)</b>	30 Microns/Coat
<b>RECOMMENDED WFT RANGE (WET FILM THICKNESS)</b>	125 Microns/Coat
<b>FLASH POINT</b>	28°C
<b>FLEXIBILITY</b>	Good
<b>ABRASION RESISTANCE</b>	Good
<b>WEATHER RESISTANCE</b>	Good



## TECHNICAL DATA SHEET

### DRYING TIME

Drying time @ 30°C (Temperature, humidity, air movement, film thickness and number of coats all affect the drying time).	
<b>TOUCH DRY</b>	1 hour
<b>DRY TO RECOAT</b>	4 hours
<b>FULLY CURED</b>	<p>1. The product cures by a gradual rise in temperature. The following cure schedule is recommended:</p> <ul style="list-style-type: none"> <li>- 30 minutes gradual rise to 100°C</li> <li>- 1 hour gradual rise to 200°C</li> <li>- 2 hour rise to 450°C</li> </ul>

### ADVANTAGES

<b>AMBER ALUMINIUM H.T. 600°C</b>	Single component aluminium paint. Dried film has excellent adhesion on metal surface, along with superior oil resistance and heat resistance up to 600°C.
-----------------------------------	---

### APPLICATION INSTRUCTION

<b>SURFACE PREPARATION</b>	Surface is to be blast cleaned to Sa2.5 to obtain maximum heat resistance
----------------------------	---

### APPLICATION DATA

<b>APPLICATION METHOD</b>	Airless Spray Conventional Spray Brush
<b>CLEANING/THINNING</b>	Amber G.P. Thinner
<b>THINNER (VOLUME)</b>	Ready to use
<b>CONV. SPRAY REQUIREMENTS</b>	Atomizing pressure: 40 psi
<b>AIRLESS SPRAY REQUIREMENTS</b>	Pressure: 2200 psi.
<b>NOZZLE SIZE</b>	0.016" – 0.018"
<b>MIXING RATIO (BY VOLUME)</b>	Not applicable
<b>POT LIFE @ 30°C (100 ml)</b>	Not applicable



## TECHNICAL DATA SHEET

### SYSTEM

<b>RECOMMENDED SYSTEM</b> To be applied on prepared surface.	Amber Aluminium H.T. 600°C	2 x 30

### ADDITIONAL DATA

<b>SHELF LIFE @ 30°C</b>	6 months, in original sealed container, with proper storage conditions.
--------------------------	---

### HEALTH & SAFETY

<b>SAFETY PRECAUTIONS</b>	<p>As a general rule, avoid skin and eye contact by wearing overalls, gloves, goggles, and airmask etc. Spillage on skin should immediately be removed by thorough washing with water and soap or suitable cleaner. Eye should be flushed with fresh water. Avoid inhalation of vapours and paint mist by wearing suitable airmask. In the event of ingestion and eye contact, seek medical attention immediately. Painting must be carried out in well-ventilated area. This as industrial product contains flammable materials and should be kept away from the sparks and open flames, smoking in the area should not be permitted. Local safety regulations should be followed.</p>
---------------------------	---



## TECHNICAL DATA SHEET

### STORAGE & HANDLING

<b>STORAGE</b>	Store the paint in proper storage conditions as per the local regulations. Keep the paint container in sealed condition under shed, away from direct sunlight and extreme temperatures. Do not stock paint material near to any ignition sources. Do not put back the half or unused material back in original container, containing the supplied paint, to avoid contamination. Handle with care. Stir well before use.
----------------	--