

TECHNICAL DATA SHEET

AMBER GUARD S.T.

PRODUCT DESCRIPTION	Amber Guard S.T. is a two pack surface tolerant, high solids
	polyamine cured epoxy based coating. It is specially
	recommended for surfaces, where optimum pretreatment is not
	feasible. It has good adhesion on various surfaces. It provides
	excellent corrosion protection in salt as well as neutral fresh
	water. It is self priming and has good abrasion resistance also.

I KECOMMENDED USES	Amber Guard S.T. is a two pack surface tolerant, high solids
	polyamine cured epoxy based coating. It is specially
	recommended for surfaces, where optimum pretreatment is not
	feasible. It has good adhesion on various surfaces. It provides
	excellent corrosion protection in salt as well as neutral fresh
	water. It is self priming and has good abrasion resistance also.

TECHNICAL DATA

COLOUR, DRY FILM	Aluminium (Silver) or Grey
FINISH, DRY FILM	Semi-glossy
VOLUME SOLIDS (ASTM D2697)	$85 \pm 2\%$
SPECIFIC GRAVITY	2.00 ± 0.05 (of mix)
THEORETICAL SPREADING	8.5 – 2.8 M2 /LTR
RECOMMENDED DFT (DRY FILM)	100 – 300 Microns/Coat
RECOMMENDED WFT (WET FILM)	118 – 355 Microns/Coat
FLASH POINT	25°C
FLEXIBILITY	Good
WATER RESISTANCE	Very good
CHEMICAL RESISTANCE	Good
SOLVENT RESISTANCE	Good
ABRASION RESISTANCE	Good





TECHNICAL DATA SHEET

DRYING TIME

Drying time @ 30°C (Temperature, humidity, air movement, film thickness and number of coatsall affect the drying time).	
TOUCH DRY 2 hours	
DRY TO RECOAT	12 hours (minimum)
FULLY CURED	3 days

ADVANTAGES

AMBER GUARD S.T.	Self-priming, with good resistance against abrasion. The fully cured film has good adhesion on various surfaces. The applied
	coating can be overcoated with chlorinated rubber epoxy or polyurethane topcoat.

APPLICATION INSTRUCTION

	A power tool cleaning to a min. St2 is recommended for surface
SURFACE PREPARATION	preparation. Improved surface treatment will improve the
	performance. When used over old coating systems, the surface
	must be sound clean and dry.

APPLICATION DATA

APPLICATION METHOD	Airless Spray	Brush or Roller
CLEANING/THINNING	Amber Epoxy Thinner (thinner should be added after mixing the component)	
THINNER (VOLUME)	5 – 10%	10%
CONV. SPRAY REQUIREMENTS	Atomizing Pressure : 50 psi	
AIRLESS SPRAY REQUIREMENTS	2200 psi	
NOZZLE SIZE	0.025" – 0.030"	
MIXING RATIO (FOR CLEAR) BY WEIGHT	Base : Hardener 1.5 : 1 (mix thoroughly, keep 10 – 15 minutes)	
POT LIFE @ 30°C (100 ml)	2 – 3 hours (reduced at higher temperature)	
	Note: Material may gel at elevated temperature	





TECHNICAL DATA SHEET

SYSTEM

RECOMMENDED SYSTEM	No. of Coats x DFT (Microns)	
To be applied on prepared surface.	Amber Guard S.T.	2 x 200
	If required can be overcoated with Amber Guard Topco Amber Polyurethane Topcoat	oat or

ADDITIONAL DATA

HEALTH & SAFETY

SAFETY PRECAUTIONS	As a general rule, avoid skin and eye contact by wearing overalls, gloves, goggles, and airmask etc. Spillage on skin should immediately be removed by thorough washing with water and soap or suitable cleaner. Eye should be flushed with fresh water. Avoid inhalation of vapours and paint mist by wearing suitable airmask. In the event of ingestion and eye contact, seek medical attention immediately. Painting must be carried out in well-ventilated area. This as industrial product, contains flammable materials and should be kept away from the sparks and open flames, smoking in the area should not be permitted. Local safety regulations should be followed.
--------------------	---

STORAGE & HANDLING

regulations. Keep the paint container in sealed condition under shed, away from direct sunlight and extreme temperatures. Do not stock paint material near to any ignition sources. Do not put back the half or unused material back in original container, containing the supplied paint, to avoid contamination. Handle with care. Stir well before use.

Store the paint in proper storage conditions as per the local

شركة دانة التاج التجارية (الثقافة الأصباغ والعام 1870 الأصباغ والعام 1871 المام 1871 ال