

## دهان ديكسي اكريليك نظامين

### الوصف :

دهان ميني على اساس مزدوج التركيب اساسه النيتروسانييت المقوى براتنجات الاكريليك ، دهان سهل الاستعمال ، سريع الجفاف ، مقاوم للظروف الجوية المختلفة ، مقاوم للاحماض و القلويات ، ذو تغطية عالية ، مقاوم للخدش و الصدمات ، ذو لمعية عالية .

### الاستخدام :

كوجه نهائي للسيارات .

### المواصفات الفنية :

|            |                                |                         |
|------------|--------------------------------|-------------------------|
|            | المظهر العام :                 | سطح لامع املس           |
|            | اللزوجة :                      | 240 – 300 ثانية         |
|            | الوزن النوعي :                 | 0.98 – 1.24 غم / مل     |
| ISO -3215  | نسبة المواد الصلبة بعد الخلط : | لا تقل عن 55%           |
| حسب اللون  | معدل التغطية :                 | 12 م <sup>2</sup> /لتر  |
|            | وقت الجفاف :                   | للمس : 30 دقيقة         |
|            |                                | بصلابة : 180 دقيقة      |
| ISO - 2813 | اللمعية على زاوية 60 :         | لا تقل عن 90 وحدة لمعية |

### التعبئة :

1 لتر / 3 لتر / 3.5 لتر

### طريقة التطبيق :

|                              |                   |
|------------------------------|-------------------|
| طريقة الاستخدام:             | بالرش             |
| طريقة الرش :                 | بالضغط 2200 P.S.I |
| نوع المخفف / تنظيف الادوات : | ثنر شامبيون       |
| فوهة فرد الرش :              | "0.021 - "0.015   |

### تهيئة السطح :

ان يكون السطح نظيفا و جافا .

### شروط التخزين :

- على درجة حرارة الغرفة بعيدا عن درجات الحرارة العالية و الرطوبة .
- يتم اضافة المقوي الخاص بنسبة 1:2 و من ثم يخفف و يرش .
- يجب استعمال الخليط خلال 5 ساعات كحد اقصى بعد اضافة المقوي على درجة حرارة 25س

### الصلاحيّة :

صالح لغاية 12 شهر كحد ادنى

## DIXIE 2K ACRYLIC PAINT

### DESCRIPTION :

DIXIE acrylic paint is two pack ,glossy topcoat which is quick drying excellent resistance to weather changes, excellent color retention , high impact and scratch resistance , mix with DIXIE hardener .

### RECOMANDED USE :

Top coat on all vehicles surfaces .

### TECHINCAL INFORMATION :

|                    |                             |                          |
|--------------------|-----------------------------|--------------------------|
| COLORS:            | White or as pre shade chart |                          |
| FINISH :           | Glossy smooth surface       |                          |
| VISCOSITY:         | 240- 300 Sec/25°C           |                          |
| SPECIFIC GRAVITY : | 0.98 -1.24 g/ml             |                          |
| SOLID CONTENT :    | Not less than 55%           | ISO - 3215               |
| COVERAGE RATE      | 18m <sup>2</sup> /LTR       | Depending on the surface |
| DRYING TIME :      | Touch dry 30mints           |                          |
|                    | Hard dry 180mints           |                          |
| GLOSSY :           | Not less 90 unit            | ISO – 2813               |

### APPLICATION DATA :

|                                  |                        |
|----------------------------------|------------------------|
| APPLICATION METHOD:              | Spray                  |
| GUIDING DATA FOR AIRLESS SPRAY : | Pressure at 2200 P.S.I |
| THINNER /CLEANING OF TOOLS :     | DIXIE thinner          |
| NOZZLE TIP :                     | 0.015"-0.021"          |

### SURFACE PREPRATION:

Surface should be clean and dry . and free from oil , grease and other dirt's .

### STORAGE CONDITION :

At room temperature away from sun rays and humidity .

### PACKAGE SIZE :

1LTR / 3LTR/ 3.5LTR

### SHELF LIFE :

Not less than 12 months from the production date .