

## معجونة ديكسي بوليستر

### الوصف :

معجونة مركبة على اساس من البولي ايستر و مجموعة من المواد المألثة ذات الجودة و النوعية العالية ، معجونة سهلة المد ، سهلة الحف ، تعطي سطح املس ناعم خالي من التشققات ، ذات معدل فرش عالي و معدل تغطية عالي للمسامات ، ذات مقاومة عالية للخدش و الصدمات .

### الاستخدام :

تستخدم على الاسطح المعدنية مثل السيارات و الاثاث المعدني .

### المواصفات الفنية :

اللون :	سكني ، اصفر ، زهري
المظهر العام :	سطح املس مطفي قابل للحف
نسبة المواد الصلبة :	100%
معدل التغطية :	حسب سماكة السطح المطلوب
وقت الجفاف :	للمس خلال 25 دقيقة
	بصلابة خلال 24 ساعة
	للحف خلال 45 دقيقة

### التعبئة :

1 لتر / 2 لتر / 3 لتر

### طريقة التطبيق :

طريقة الاستخدام:	باستخدام المالج او سكين مد خاص
نوع المخفف / تنظيف الادوات :	جاهزة للاستعمال

### تهيئة السطح :

ان يكون السطح نظيفا و جافا .

### شروط التخزين :

على درجة حرارة الغرفة بعيدا عن درجات الحرارة العالية و الرطوبة

### الصلاحية :

صالح لغاية 12 شهر كحد ادنى ، يجب استخدام المعجونة خلال 30 دقيقة من اضافة الهاردنر .

### نسبة الخلط :

يجب اضافة 2% من وزن المعجونة هاردنر .

**DIXIE POLYESTER PUTTY  
BODY FILLER**

**DESCRIPTION :**

Polyester putty is made of an out standing resin with top quality fillers formulated to give a putty which dries quickly , to give smooth strong surface ready for priming , it has the minimum shrinking volume and minimum plugging of the sanding papers with no bleeding through the upper coat .

**RECOMANDED USE :**

As body filler on metal surfaces mainly vehicles.

**TECHINCAL INFORMATION :**

<b>COLORS:</b>	Gray , Yellow , Rose	
<b>FINISH :</b>	Sandable matt surface	
<b>VISCOSITY:</b>	Paste	
<b>SOLID CONTENT :</b>	100%	
<b>DRYING TIME :</b>	Touch dry 25mints	
	Hard dry 24 hrs	

**APPLICATION DATA :**

<b>APPLICATION METHOD:</b>	Special knife
<b>THINNER /CLEANING OF TOOLS :</b>	DIXIE thinner

**SURFACE PREPRATION:**

Surface should be clean and dry .

**STORAGE CONDITION :**

At room temperature away from sun rays and humidity .

**PACKAGE SIZE :**

**1 LTR / 2LTR /3LTR**

**SHELF LIFE :**

Not less than 12 months from the production date , when hardener is added the putty should be used during 30 mints

**MIXING RATIO :**

Mix with curing agent by a ratio of 100 part polyester putty to 2 parts curing agent directly before use .