

## NATIONAL GRAFFITO (TEXTURED COATING)

| DESCRIPTION | National Graffito is an acrylic copolymer emulsion based texture         |
|-------------|--|
|             | finish, reinforced with specific graded hard aggregates and pigments.    |
|             | It is specially formulated to withstand the high humid and extreme       |
|             | hot climate of the Gulf. It can hide and protect minor surface           |
|             | imperfections and hairline cracks on the substrate. It is a flexible,    |
|             | tough and weather resistant coating for interior/exterior surfaces. It   |
|             | has a special grooved-graffio finish having excellent adhesion and       |
|             | alkali resistance. It contains anti fungal and anti bacterial additives. |
|             |  |

| <b>RECOMMENDED USES</b> | National Graffito is recommended for special grooved-graffito finish    |
|-------------------------|---|
|                         | interior/exterior decorative applications. Over coating with National   |
|                         | thane, National Acrylic Rock Topcoats, National Gloss Emulsion etc.     |
|                         | will reduce dust collection and improve durability. It is suitable for  |
|                         | the application on concrete, plaster, gypsum, asbestos, brickwork,      |
|                         | wood etc. It is mostly used for the application of internal/external    |
|                         | walls of flats, buildings, villas, museums, exhibition center, boundary |
|                         | walls etc.  |
|                         |   |

## TECHNICAL DATA

| COLOUR, DRY FILM       | White & off White  |
|------------------------|--|
| FINISH, DRY FILM       | Grooved-Graffito finish / Matt                                 |
| VOLUME SOLIDS          | $71 \pm 2\%$   |
| (ASTM D2697)           |  |
| SPECIFIC GRAVITY       | $1.85 \pm 0.05$  |
| THEORETICAL SPREADING  | $0.7 - 0.6 \text{ M}^2/\text{LTR}$ (Depends on aggregate size) |
| <b>RECOMMENDED DFT</b> | 1000 – 1200 Microns/Coat                                       |
| (DRY FILM)             |  |
| <b>RECOMMENDED WFT</b> | 1400 – 1700 Microns/Coat                                       |
| (WET FILM)             |  |
| FLASH POINT            | Water Base   |

## **DRYING TIME**

Drying time @ 30°C (Temperature, humidity, air movement, film thickness and number of coats all affect<br/>the drying time).TOUCH DRY2 – 3 hoursFULL DRY48 hours



## **ADVANTAGES**

| NATIONAL GRAFFITO   | Excellent adhesion and alkali resistance withstands extreme climate of the gulf, hides minor surface imperfections and |
|---------------------|--|
|                     | hairline cracks, flexible and tough weather resistant coating.   |
| SURFACE PREPARATION | Before application, the surface should be sound, clean and   |
|                     | free from oil, grease, loose particles, dust, etc. Application   |
|                     | can be done by the recommended application methods.  |

1/2

|  | APPLICATION DATA  |
|--|---|
| APPLICATION METHOD   | Special Trowel / Airless Spray  |
| CLEANING/THINNING  | Water   |
| THINNER (VOLUME)   | Max. 5% water   |
|  | <u>SYSTEM</u>   |
| <b>RECOMMENDED SYSTEM</b><br>To be applied on prepared<br>surface. | National Acrylic Primer (W.B.): 1 coat  |
|  | National Graffito : 1 coat  |
|  | Other National recommended topcoat (if required) : 2 coat   |
|  | ADDITIONAL DATA   |
| SHELF LIFE @ 30°C  | 36 months in original sealed container, with proper storag conditions.  |
|  | HEALTH & SAFETY   |
| SAFETY PRECAUTIONS   | Generally, most of the water base paints are quite safe to handle with<br>due precautions. As a general rule, avoid skin and eye contact b<br>wearing overalls, gloves, goggles, and mask etc. Spillage on ski<br>should immediately be removed by thorough washing with water an<br>soap or suitable cleaner. Eyes should be flushed with fresh wate<br>Avoid inhalation of vapors and paint mist by wearing a suitable mask.<br>In the event of ingestion and eye contact, seek medical attentio<br>immediately. Painting must be carried out in a well-ventilated area<br>Local safety regulations to be followed. |
|  | STORAGE & HANDLING  |
| STORAGE  | Store the paint in proper storage conditions as per the local<br>regulations. Keep the paint container in a sealed condition in the<br>shade, away from direct sunlight and extreme temperatures. Do not<br>keep paint material near any ignition sources. Do not put back the<br>half or unused material back in the original container containing the<br>supplied paint, to avoid contamination. Handle with care. Stir well<br>before use.   |
|  |   |

**NOTE:** We warranty the quality of our product and this data sheet represents test results and practical experience obtained under controlled conditions. We reserve the right to change data without prior notice.