

NATIONAL GUARD ZINC RICH EPOXY PRIMER PROTECTIVE COATINGS

USES

TECHNICAL DATA SHEET

NATIONAL GUARD ZINC RICH EPOXY PRIMER

PRODUCT DESCRIPTION	A two-pack zinc rich polyamide cured epoxy primer with metallic zinc powder. It provides a tough resistant coating with excellent mechanical and anti-corrosive properties. It provides cathodic protection on a local mechanical damage. It also has excellent adhesion on metal surfaces.
RECOMMENDED	Anti-corrosive primer for structural steel in fertilizer plants,

OMMENDED	Anti-corrosive primer for structural steel in fertilizer plants,
5	piping and petrochemical sub oil structures and parts immersed
	in water. The super imposed system must be unsopanifiable

TECHNICAL DATA

	C
COLOUR, DRY FILM	Grey
FINISH, DRY FILM	Smooth / Matt
VOLUME SOLIDS	$51 \pm 2\%$
(ASTM D2697)	
SPECIFIC GRAVITY	2.40± 0.05 (of mix)
THEORETICAL SPREADING	$20.4 - 10.2 \text{ M}^2/\text{LTR}$
RANGE	
RECOMMENDED DFT RANGE	25 – 50 Microns/Coat
(DRY FILM THICKNESS)	
RECOMMENDED WFT RANGE	49 – 98 Microns/Coat
(WET FILM THICKNESS)	
FLASH POINT	24°C
FLEXIBILITY	Fair
WATER RESISTANCE	Excellent
SOLVENT RESISTANCE	Very Good
ADHESION	Excellent
ABRASION RESISTANCE	Good

DRYING TIME

Drying time @ 30°C (Temperature, humidity, air movement, film thickness and number of coats all affect the drying time.)		
TOUCH DRY 30 minutes		
*DRY TO RECOAT / OVERCOAT 6 hours (minimum) – For maximum recoating interval refer		
our Technical service division.		
FULLY CURED 5 days		

*For same generic type paint.





NATIONAL GUARD ZINC RICH EPOXY PRIMER PROTECTIVE COATINGS

TECHNICAL DATA SHEET

ADVANTAGES

NATIONAL GUARD ZINC RICH	It provides a tough resistant coating with excellent mechanical
EPOXY PRIMER	and anti-corrosive properties. Provides cathodic protection on a
	local mechanical damage, excellent adhesion on properly
	cleaned surface.

APPLICATION INSTRUCTION

SURFACE PREPARATION	Oil and grease should be removed by solvent cleaning. Sand	
	blast to Sa 2.5, then clean & dry. Apply immediately National	
	Guard Epoxy Red Oxide Primer after the steel has been	
	blasted.	
REPAIR		
	Corroded areas should be power tool cleaned to St3 or blast	
	cleaned to Sa2 or better. Existing system should be dry and	
	free from loose paint, salt, grease and other contaminants prior	
	to overcoating.	

APPLICATION DATA

APPLICATION METHOD	Airless Spray	Conventional Spray	Brush
CLEANING/THINNING	National Epoxy Thinner		
THINNER (VOLUME)	5 - 10%	10-15%	5 - 10%
CONV. SPRAY REQUIREMENTS	Atomizing Pressure :	40 psi	
AIRLESS SPRAY REQUIREMENTS	2200 psi		
NOZZLE SIZE	0.018" – 0.020"		
MIXING RATIO (BY VOLUME)	Base : Hardener		
	4 : 1 (Mix thoroughly, keep for $10 - 15$ minutes)		
POT LIFE @ 30°c (100 ml)	8 hours (reduced at higher temperature)		
	Note: Material may gel at elevated temperature.		

SYSTEM

	No. of Coats x	DF	Γ (Microns)
RECOMMENDED SYSTEM To be applied on prepared surface.	National Guard Zinc Rich Epoxy Primer	:	1 x 30
	National Guard Undercoat H.B.	:	1 x 125
	National Guard Topcoat (OR)	:	1 x 50
	National Polyurethane Topcoat (OR)		
	as specified	:	1 x 40

www.national-paints.com





NATIONAL GUARD ZINC RICH EPOXY PRIMER PROTECTIVE COATINGS

TECHNICAL DATA SHEET

ADDITIONAL DATA

SHELF LIFE @ 30°C	18 months, in original sealed container, with proper storage
	conditions.

HEALTH & SAFETY

SAFETY	As a general rule, avoid skin and eye contact by wearing
PRECAUTIONS	overalls, gloves, goggles, and airmask etc. Spillage on skin
	should immediately be removed by thorough washing with
	water and soap or suitable cleaner. Eye should be flushed with
	fresh water. Avoid inhalation of vapours and paint mist by
	wearing suitable airmask. In the event of ingestion and eye
	contact, seek medical attention immediately. Painting must be
	carried out in well-ventilated area.
	This as industrial product, contains flammable materials and
	should be kept away from the sparks and open flames, smoking
	in the area should not be permitted. Local safety regulations
	should be followed.

STORAGE & HANDLING

STORAGE	Store the paint in proper storage conditions as per the local
	regulations. Keep the paint container in sealed condition under
	shed, away from direct sunlight and extreme temperatures. Do
	not stock paint material near to any ignition sources. Do not put
	back the half or unused material back in original container,
	containing the supplied paint, to avoid contamination. Handle
	with care. Stir well before use.

NOTE: We warranty only the quality of our product and this data sheet is based on results obtained from experience and tests. We reserve the right to change data without prior notice. For surface preparation, safety details refer specifier and safety data.

This data sheet supersedes all previous issued. Issued: 0608

