



Technical Data Sheet

DIXIE N.C. GOLD

DESCRIPTION

Dixie N.C. Gold is fast drying nitrocellulose based topcoat. It has a good resistance to water and general chemical properties. It is designed with a distinct and brilliant metallic golden finish.

USES

Dixie N.C. Gold gives an aesthetic golden lustre finish for wooden and metal furniture applications and can be applied on the following substrates:

- Wooden substrates
- Synthetic wooden substrates like veneer, particle board, MDF, HDF and OST
- Metal substrates

ADVANTAGES

- Easy to apply
- Quick drying
- Excellent hardness
- Uniform spreading
- Aesthetic metallic golden finish

TYPICAL PROPERTIES

• Color & Appearance	
Color of Dry Film	Metallic, Golden
Finish Dry Film	Metallic Lustre
• Specific Gravity	1.00 ± 0.05
• Volume Solids (ASTM D 2697)	28 ± 2%
• Film Thickness	
Wet Film Thickness (WFT)	70 – 110 microns/coat
Dry Film Thickness (DFT)	20 – 30 microns/coat
• Drying Time	
Touch Dry @ 30°C	10 - 15 minutes
Dry to Recoat @ 30°C	2 - 3 hours
Dry to Hard Dry @ 30°C	8 - 15 hours
• Theoretical Spreading Rate	14 – 9 m ² /liter
• Flash Point	10°C

PACKAGING SIZE

- 0.9 liters
- 3 liters
- 15 liters



Technical Data Sheet

SURFACE PREPARATION

- The surface to be coated should be clean, free from contamination and suitably primed.
- Sand the primed surface with 320 and 400 emery paper.
- It is recommended to apply the top coat on a moisture free surface (moisture content less than 10%).

APPLICATION METHOD

- **Brush**
- **Spray (conventional)**
 - Airless Spray Requirements
 - Pressure: 2100 psi
 - Nozzle Size: 0.018" – 0.020"
- **Cleaning solvent/Thinner:** Dixie Lacquer Thinner
- **Dilution by volume :** 1:1 (Paint : thinner)

SAFETY PRECAUTIONS

- Avoid skin and eye contact by wearing overalls, gloves, goggles, and mask etc.
- **Skin Contact:** Clean with recommended thinner first and then wash thoroughly with soap and water. Seek medical attention if any irritation persists.
- **Eye contact:** In the event of accidental splashes, flush eye with water and rinse thoroughly. Seek medical advice immediately.
- Avoid inhalation of vapors and paint mist by wearing suitable mask.
- In the event of ingestion seek medical attention immediately.
- Application must be carried out in well-ventilated area.
- This product contains flammable materials and should be kept away from the sparks and open flames.
- Smoking in the area should not be permitted.
- Local safety regulations need to be followed.

RECOMMENDED SYSTEM

Dixie N.C. Primer Surfacer	1 - 2 coats
Dixie Polyester Putty or Dixie N.C. Putty	1 coat
Dixie N.C. Primer Surfacer	1 - 2 coats
Dixie N.C. Gold	2 coats
Dixie N.C. Auto Lacquer Clear	1 coat

STORAGE & SHELF LIFE

- Store the material in proper storage conditions as per the local regulations. Keep the paint container in sealed condition under shed, away from direct sunlight, extreme temperature and avoid exposure to moisture .
- Do not keep paint material near to any ignition sources.
- Do not put back the half or unused material back in original container, containing the supplied paint, to avoid contamination.
- Handle with care.
- Stir well before use.
- Shelf life at 30°C is 24 months in original sealed container with proper storage conditions.

NOTE: We warranty only the quality of our product and this data sheet is based on results obtained from experience and tests. We reserve the right to change data without prior notice. For safety details kindly refer safety data sheet.